



WORK TEST CERTIFICATE

53 Grade Ordinary Portland Cement

Despatched during Week No.		13	From 26-03-2019		3-2019	То	01-04-2019	
Test Certificate No.		13	Referenc	e No		WCW/IMS/QA/FM/08		
Dated		30-04-2019		Je No.		WCW/IIWS/QA/I W/00		
S.N.	Parameters			Results Obtained	Requirement as per IS 269 : 2015 (Variety: OPC 53)			
1	Chemical Composition							
	Lime Saturation Factor (CaO – 0.7 *SO ₃₎ / (2.8* SiO ₂ + 1.2* Al ₂ O ₃ + 0.65* Fe ₂ O ₃)			0.90	Not greater than 1.02 and not less than 0.80			
	Ratio of % Alumina to that of Iron Oxide Al_2O_3 / Fe_2O_3			1.28	Not less than 0.66			
	Insoluble Residue (% by mass)			0.50	Not more than 5.0 %			
	Magnesia (% by mass)			1.00	Not more than 6.0 %			
	Sulphuric Anhydride (% by mass)			3.00	Not More than 3.5 %			
	Total loss on Ignition (%)			1.50	Not More than 4.0 %			
	Chloride Content (%)			0.013	Not more than 0.1 % for general purpose & not more than 0.05 % for pre-stressed structures			
	Physical Analysis			•				
2	Fineness							
	Blaine's Specific Surface Area (m ² / kg)			311	Not Less than 225			
3	Compressive Strength							
	72 ± 1h (3 Days)			36.4	Not less th	Not less than 27.0		
	168 ± 2h (7 Days)			46.8	Not less than 37.0			
	672 ± 4h (28 Days) *			59.4	Not less than 53.0			
4	Setting Time (Minutes							
	Initial			135	Not less th	less than 30		
	Final	inal			Not more than 600			
5	Soundness							
	Le-Chatelier Expansion (mm)			2.00	Not more than 10.0			
	Auto-Clave Expansion (%)			0.140	Not more than 0.8			
6	Normal Consistency (%)			27.50				
	Temp. During Testing (⁰ C)			27.00	(27 ± 2)°C			

The above cement complies with the requirements of IS 269 : 2015 (Variety: OPC 53) for 53 Grade Ordinary Portland Cement

Manager (QA)