



## **53 Grade Ordinary Portland Cement**

Despatched during Week No.		14	From	02/04/19		То	08/04/19	
Test Certificate No.		14	Referenc	e No.		WCW/IMS/QA/FM/08		
Dated		07/05/19	relefenc					
S.N.	Parameters			Results Obtained	Requirement as per IS 269 : 2015 (Variety: OPC 53)			
1	Chemical Composition							
	Lime Saturation Factor ( $CaO - 0.7 *SO_3$ ) / $(2.8* SiO_2 + 1.2* Al_2O_3 + 0.65* Fe_2O_3)$			0.90	Not greater than 1.02 and not less than 0.80			
	Ratio of % Alumina to that of Iron Oxide Al <sub>2</sub> O <sub>3</sub> / Fe <sub>2</sub> O <sub>3</sub>			1.31	Not less than 0.66			
	Insoluble Residue (% by mass)			0.60	Not more than 5.0 %			
	Magnesia (% by mass)			1.00	Not more than 6.0 %			
	Sulphuric Anhydride (% by mass)			2.98	Not More than 3.5 %			
	Total loss on Ignition (%)			1.30	Not More than 4.0 %			
	Chloride Content (%)			0.014	Not more than 0.1 % for general purpose & not more than 0.05 % for pre-stressed structures			
	Physical Analysis				•			
2	Fineness							
	Blaine's Specific Surface Area (m² / kg)			295	Not Less than 225			
3	Compressive Strength							
	72 ± 1h (3 Days)			38.0	Not less than 27.0			
	168 ± 2h (7 Days)			47.5	Not less than 37.0			
	672 ± 4h (28 Days) *			61.1	Not less than 53.0			
4	Setting Time (Minutes)							
	Initial			145	Not less th	t less than 30		
	Final	inal			Not more than 600			
5	Soundness							
	Le-Chatelier Expansion (mm)			1.00	Not more than 10.0			
	Auto-Clave Expansion (	to-Clave Expansion (%)			Not more than 0.8			
6	Normal Consistency (%	ıl Consistency (%)						
	Temp. During Testing (°C)			27.00	$(27 \pm 2)^{\circ}$ C			

The above cement complies with the requirements of IS 269 : 2015 (Variety: OPC 53) for 53 Grade Ordinary Portland Cement

Manager (QA)