





WORK TEST CERTIFICATE

	53 Gra	de Ordii	nar	y Poi	rtland Cem	ent		
Despatched during Week No.		21		From	21/05/2017	То	27/05/2017	
Test Certificate No. Dated		21 27/06/201					/D/LAB/TC/07	
S.N.	Parameters			ResultsRequirement as perbtainedIS 269 : 2015 (Variety: OPC 53)		•		
1	Chemical Composition							
	Lime Saturation Factor CaO - 0.7 SO ₃ / (2.8 SiO ₂ + 1.2 Al ₂ O ₃ + 0.65 Fe ₂ O ₃)		0.90		Not greater than 1.02 and not less than 0.80			
	Ratio of % Alumina to that of Iron Oxide AI_2O_3 / Fe_2O_3		1.31		Not less than 0.66			
	Insoluble Residue (% by mass)		0.4		Not more than 5.0 %			
	Magnesia (% by mass)		0.8		Not more than 6.0 %			
	Sulphuric Anhydride (% by mass)		2	2.8	Not More than 3.5 %			
	Total loss on Ignition (%)		1	L.7	Not More than 4.0 %			
	Chloride Content (%)		0.021 Not More than 0.1 % for general purpose but more than 0.05 % for pre-stressed structure		neral purpose but not ressed structures			
	Physical Analysis							
2	Fineness							
	Blaine's Specific Surface Area (m ² / kg)		3	10	Not Less than 225			
3	Compressive Strength (MPa)							
	72 ± 1h (3 Days)		3	7.0	Not less than 27.0			
	168 ± 2h (7 Days)		4	7.0	Not less than 37.0			
	672 ± 4h (28 Days) *		5	8.8	Not less than 53.0			
4	Setting Time (Minutes)							
	Initial		135 Not less		Not less than 30	than 30		
	Final		1	.95	Not more than 600			
5	Soundness							
	Le-Chatelier Expansion (mm)		1	l.1	Not more than 10.0			
	Auto-Clave Expansion (%)		0	.09	Not more than 0.8			
6	Normal Consistency (%)		2	7.1				
	Temp. During Testing (⁰ C)		2	27 $(27 \pm 2)^{0}$ C				

The above cement complies with the requirements of IS 269: 2015 (Variety: OPC 53) for 53 Grade Ordinary Portland Cement

Parcher 1

Manager (QA)

Chief Manager -QC