



53 Grade Ordinary Portland Cement

Despatched during Week No.		24	From	11-06-2019		То	17-06-2019
Test Certificate No.		16-07-2019 Reference		e No.		WCW/IMS/QA/FM/08	
Dated							
S.N.	Pa	rameters	Results Obtained Requirement as per IS 269 : 2015 (Variety: OPC 53)				
1	Chemical Composition						
	Lime Saturation Factor (CaO – 0.7 *SO ₃ / (2.8* SiO ₂ + 1.2* Al ₂ O ₃ + 0.65* Fe ₂ O ₃)			0.91	Not greater than 1.02 and not less than 0.80		
	Ratio of % Alumina to that of Iron Oxide Al ₂ O ₃ / Fe ₂ O ₃			1.23	Not less than 0.66		
	Insoluble Residue (% by mass)			0.60	Not more than 5.0 %		
	Magnesia (% by mass)			0.90	Not more than 6.0 %		
	Sulphuric Anhydride (% by mass)			3.10	Not More than 3.5 %		
	Total loss on Ignition (%)			1.90	Not More than 4.0 %		
	Chloride Content (%)			0.014	Not more than 0.1 % for general purpose & not more than 0.05 % for pre-stressed structures		
	Physical Analysis			•	•		
2	Fineness						
	Blaine's Specific Surface Area (m² / kg)			298	Not Less than 225		
3	Compressive Strength						
	72 ± 1h (3 Days)			36.8	Not less than 27.0		
	168 ± 2h (7 Days)			47.2	Not less than 37.0		
	672 ± 4h (28 Days) *			59.1	Not less than 53.0		
4	Setting Time (Minutes)						
	Initial			130	Not less than 30		
	Final			185	Not more than 600		
5	Soundness						
	Le-Chatelier Expansion (mm)			1.50	Not more than 10.0		
	Auto-Clave Expansion (%)			0.130	Not more than 0.8		
6	Normal Consistency (%)			27.30			
	Temp. During Testing (°C)			27.00	(27 ± 2) ⁰ C		

The above cement complies with the requirements of IS 269 : 2015 (Variety: OPC 53) for 53 Grade Ordinary Portland Cement

Manager (QA)