





53 Grade Ordinary Portland Cement

Despatched during Week No.		4	From	22/0	1/19	То	28/01/19
Test Certificate No. Dated		4	Deference	o No	Ne		WINE OA (EN IOS
		26/02/19 Reference		∋ NO.		WCW/IMS/QA/FM/08	
S.N.	Pa	rameters		Results Obtained	Requirement as per IS 269 : 2015 (Variety: OPC 53)		
1	Chemical Composition						
	Lime Saturation Factor (CaO – 0.7 *SO ₃) / (2.8* SiO ₂ + 1.2* Al ₂ O ₃ + 0.65* Fe ₂ O ₃)			0.91	Not greater than 1.02 and not less than 0.80		
	Ratio of % Alumina to that of Iron Oxide Al ₂ O ₃ / Fe ₂ O ₃			1.28	Not less than 0.66		
	Insoluble Residue (% by mass)			0.60	Not more than 5.0 %		
	Magnesia (% by mass)			1.00	Not more than 6.0 %		
	Sulphuric Anhydride (% by mass)			2.90	Not More than 3.5 %		
	Total loss on Ignition (%)			1.40	Not More than 4.0 %		
	Chloride Content (%)			0.010	Not more than 0.1 % for general purpose & not more than 0.05 % for pre-stressed structures		
	Physical Analysis			•	•		
2	Fineness						
	Blaine's Specific Surface Area (m² / kg)			308	Not Less than 225		
3	Compressive Strength						
	72 ± 1h (3 Days)			37.4	Not less than 27.0		
	168 ± 2h (7 Days)			47.6	Not less than 37.0		
	672 ± 4h (28 Days) *			59.7	Not less than 53.0		
4	Setting Time (Minutes)						
	Initial			130	Not less than 30		
	Final			200	Not more than 600		
5	Soundness						
	Le-Chatelier Expansion (mm)			1.00	Not more than 10.0		
	Auto-Clave Expansion (%)			0.080	Not more than 0.8		
6	Normal Consistency (%)			27.00			
	Temp. During Testing (°C)			27.00	(27 ± 2) ⁰ C		

The above cement complies with the requirements of IS 269 : 2015 (Variety: OPC 53) for 53 Grade Ordinary Portland Cement

Manager (QA)