



ACC

WADI CEMENT WORKS

WORKS TEST CERTIFICATE

53Gr.OPC

Doc.No.:WD/LAB/FM/08

IS: 12269



CM/L - 2023022

Name & Address of the Consignee :		DATE 04.03.2016	
BULK CEMENT CORPN.(INDIA) LTD, KALAMBOLI, NEW-MUMBAI.		DESPATCH PARTICULARS :- WEEK NO- 08 (19.02.2016 to 25.02.2016)	
		Results	Requirements as per IS: 12269 : 2013
1	CHEMICAL COMPOSITION :		
	% Soluble Silica	21.3	
	% Alumina	5.1	
	% Iron Oxide	3.9	
	% Lime	63.1	
	% Magnesia	0.8	Not more than 6.0%
	% Insoluble Residue	0.4	Not more than 4.0%
	% Sulphur Calculated as SO ₃	2.7	Not more than 3.5%
	% Loss On Ignition	1.8	--- Not more than 4.0 %
	LIME SATURATION FACTOR	0.90	--- Between 0.80 & 1.02
	PROPORTION OF ALUMINA TO IRON OXIDE	1.31	--- Not less than 0.66
	TRI CALCIUM ALUMINATE	6.92	
	% CHLORIDE	0.024	--- Not more than 0.1%
2	FINESS : Specific Surface (m ² /kg)	292.0	--- Not less than 225
3	COMPRESSIVE STRENGTH (MPa) :		
	at 3-Days	38.9	--- Not less than 27
	7-Days	49.1	--- Not less than 37
	28-Days	Awaited	--- Not less than 53
4	SETTING TIME (minutes) :		
	Initial	135.0	--- Not less than 30
	Final	190.0	--- Not more than 600
5	SOUNDNESS :		
	Le-Chatelier Expn. (mm)	1.00	--- Not more than 10 mm
	Autoclave Expn. (%)	0.06	--- Not more than 0.8 %
6	a) Normal Consistency (%)	27.5	
	b) Temp.during Testing (deg.C) :	27+/-2	

ACC LIMITED
Wadi Cement Works
P.O. WADI In
Dist. Gulbarga-Karnataka
PIN : 585225

[Signature]
Chief Mgr.Q.A.

Forwarded to : CMD-MUMBAI/PUNE/B'LORE/SEC/ COIMBATORE/Solapur Dump/Laboratory