

-





Portland Pozzolana Cement

Despatched during Week No. Test Certificate No. Dated		1	From	01/0)1/19	То	07/01/19
		1	Reference			WCW/IMS/QA/FM/09	
		05/02/19					
S.N.	Pa	arameters		Results Obtained	Requirement as per IS 1489 (Part I) : 2015		
1	Chemical Composition						
	Loss on Ignition (% by mass)			2.10	Not More than 5.0 %		
	Magnesia (% by mass)			1.00	Not more than 6.0 %		
	Sulphuric Anhydride SO3 (% by mass)			2.60	Not More than 3.5 %		
	Chloride Content (% by mass)			0.01	Not more than 0.1 % for general purpose & not more than 0.05 % for pre-stressed structures		
	Insoluble Residue (% by mass)			27.30	Not More than [X + 4.0 (100-X) / 100] & Not less than (0.6 X), Where "X" is the declared Pozzolana content in cement		
	Physical Analysis			1	1		
2	Fineness						
	Blaine's Specific Surface Area (m ² / kg)			330	Not Less than 300		
3	Compressive Strength	n (MPa)					
	72 ± 1h (3 Days)			27.6	Not less than 16.0		
	168 ± 2h (7 Days)			37.2	Not less than 22.0		
	672 ± 4h (28 Days) *			56.2	Not less than 33.0		
4	Setting Time (Minutes						
	Initial			140	Not less than 30		
	Final			230	Not more than 600		
5	Soundness						
	Le-Chatelier Expansion (mm)			0.00	Not more than 10.0		
	Auto-Clave Expansion (%)			0.000	Not more than 0.8		
6	Drying Shrinkage (%)*			Awaited	Not more than 0.15		
7	Normal Consistency (%)			30.50			
	Temp. During Testing (⁰ C)			27.00	(27 ± 2) ⁰ C		

The above cement complies with the requirements of IS 1489 (Part I): 2015 for Portland Pozzolana Cement.

Cred &

Manager (QA)

Registered Office: Cement House, 121, Maharishi Karve Road, Mumbai - 400020