



WORK TEST CERTIFICATE



Portland Pozzolana Cement

Test Cer			From	10-1014	ır-2020	То	24-Mar-2020	
Test Certificate No.		12	D	- No				
Dated		22-Apr-2020	r-2020 Reference N		NO.		WCW/IMS/QA/FM/09	
S.N.	Pa	rameters	•	Results Obtained	Requirem	ent as per	IS 1489 (Part I) : 2015	
1	Chemical Composition							
	Loss on Ignition (% by mass)			1.80	Not More than 5.0 %			
	Magnesia (% by mass)			0.78	Not more than 6.0 %			
	Sulphuric Anhydride SO3 (% by mass)			2.10	Not More than 3.5 %			
	Chloride Content (% by mass)			0.01	Not more than 0.1 % for general purpose & not more than 0.05 % for pre-stressed structures			
	Insoluble Residue (% by mass)			28.30	Not More than [X + 4.0 (100-X) / 100] & Not less than (0.6 X), Where "X" is the declared Pozzolana content in cement			
	Physical Analysis				1			
2	Fineness							
	Blaine's Specific Surface Area (m2 / kg)			323	Not Less than 300			
3	Compressive Strength (MPa)							
	72 ± 1h (3 Days)			28.0	Not less than 16.0			
	168 ± 2h (7 Days)			37.6	Not less than 22.0			
	672 ± 4h (28 Days) *			56.2	Not less than 33.0			
4	Setting Time (Minutes)							
	Initial			175	Not less than 30			
	Final			260	Not more than 600			
5	Soundness							
	Le-Chatelier Expansion (mm)			1.00	Not more than 10.0			
	Auto-Clave Expansion (%)			0.040	Not more than 0.8			
6	Drying Shrinkage (%)* 0.04 Not more than 0.15							
7	Normal Consistency (%)			29.50				
	Temp. During Testing (0C)			27.00	(27 ± 2)0C			

* Fly Ash Content in Cement is (%)

34.00

The above cement complies with the requirements of IS 1489 (Part I): 2015 for Portland Pozzolana Cement.

Manager (QA)

Registered Office: Cement House, 121, Maharishi Karve Road, Mumbai - 400020