



WORK TEST CERTIFICATE



## **Portland Pozzolana Cement**

Despatched during Week No.		29	From	16-Ju	I-2019	То	22-Jul-2019
Test Certificate No.		29	Deferre				
Dated		8/20/2019	Reference No.		WCW/IMS/QA/FM/09		
S.N.	Pa	rameters		Results Obtained	per	IS 1489 (P	art I) : 2015
1	Chemical Composition						
	Loss on Ignition (% by mass)			2.04	Not More than 5.0 %		
	Magnesia (% by mass)			0.99	Not more than 6.0 %		
	Sulphuric Anhydride SO3 (% by mass)			2.56	Not More than 3.5 %		
	Chloride Content (% by mass)			0.01	Not more than 0.1 % for general purpose & not more than 0.05 % for pre-stressed structures		
	Insoluble Residue (% by mass)			28.26	Not More than [X + 4.0 (100-X) / 100] & Not less than (0.6 X), Where "X" is the declared Pozzolana content in cement		
	Physical Analysis			1	1		
2	Fineness						
	Blaine's Specific Surface Area (m2 / kg)			336	Not Less than 300		
3	Compressive Strength (MPa)						
	72 ± 1h (3 Days)			31.4	Not less than 16.0		
	168 ± 2h (7 Days)			38.8	Not less than 22.0		
	672 ± 4h (28 Days) *		58.1	Not less than 33.0			
4	Setting Time (Minutes)						
	Initial			146	Not less than 30		
	Final			219	Not more than 600		
5	Soundness						
	Le-Chatelier Expansion (mm)			0.71	Not more than 10.0		
	Auto-Clave Expansion (%)			0.036	Not more than 0.8		
6	Drying Shrinkage (%)*			Awaited	Not more than 0.15		
7	Normal Consistency (%)			31.00			
	Temp. During Testing (0C)			27.00	(27 ± 2)0C		

\* Fly Ash Content in Cement is (%)

34.00

The above cement complies with the requirements of IS 1489 (Part I): 2015 for Portland Pozzolana Cement.

Manager (QA)

Registered Office: Cement House, 121, Maharishi Karve Road, Mumbai - 400020