

* Fly Ash Content in Cement is

(%)



Wadi Cement Works



WORK TEST CERTIFICATE

Portland Pozzolana Cement

Despatched during Week No.		6	From	05-02	05-02-2019		11-02-2019	
Test Certificate No.		6	Reference No.		No.		WCW/IMS/QA/FM/09	
Dated		12-03-2019						
S.N.	Pa	rameters		Results Obtained				
1	Chemical Composition							
	Loss on Ignition (% by mass)			2.40	Not More than 5.0 %			
	Magnesia (% by mass)			0.90	Not more than 6.0 %			
	Sulphuric Anhydride SO3 (% by mass)			2.30	Not More than 3.5 %			
	Chloride Content (% by mass)			0.01	Not more than 0.1 % for general purpose & not more than 0.05 % for pre-stressed structures			
	Insoluble Residue (% by mass)			27.30	Not More than [X + 4.0 (100-X) / 100] & Not less than (0.6 X), Where "X" is the declared Pozzolana content in cement			
	Physical Analysis							
2	Fineness							
	Blaine's Specific Surface Area (m² / kg)			336	Not Less than 300			
3	Compressive Strength (MPa)							
	72 ± 1h (3 Days)			28.1	Not less than 16.0			
	168 ± 2h (7 Days)			37.4	Not less than 22.0			
	672 ± 4h (28 Days) *			56.1	Not less than 33.0			
4	Setting Time (Minutes							
	Initial			150	Not less than 30			
	Final			235	Not more than 600			
5	Soundness							
	Le-Chatelier Expansion (mm)			1.00	Not more than 10.0			
	Auto-Clave Expansion (%)			0.009	Not more than 0.8			
6	Drying Shrinkage (%)*	ing Shrinkage (%)*			Not more than 0.15			
7	Normal Consistency (%)			30.00				
	Temp. During Testing (°C)			27.00	(27 ± 2) ⁰ C			

The above cement complies with the requirements of IS 1489 (Part I): 2015 for Portland Pozzolana Cement.

Manager (QA)

34.00