





DASTAN, PALSANA, DIST. SURAT (GUJ.)

LICENCE NO. CM/L-7200051996

TEST CERTIFICATE

Customer Name & Address : Certificate (ULR) No. : TC801319000000108P

Sample Identification : Ordinary Portland Cement – 53 Grade (As per IS 269 : 2015)

Sample Date : 16.04.2019 to 22.04.2019 (Week No : 16) Date of Issue: 01.05.2019

Sr. No	Particulars	Test Method	Requirement of IS:269	Results Obtained
	Chen	nical Requirement	S	
1	Ratio of Percentage of Lime to percentage of silica, alumina and iron oxide $\text{CaO} = 0.7\text{SO}_3$	IS : 4032 - 1985	Not greater than 1.02 And not less than 0.80	0.881
	2.8 SiO ₂ + 1.2 Al ₂ O ₃ + 0.65 Fe ₂ O ₃	ļ		
2	Ratio of percentage of alumina to that of iron oxide	IS : 4032 - 1985	Not less than 0.66	1.53
3	Insoluble residue(% by mass)	IS : 4032 - 1985	Not more than 5.0	2.07
4	Magnesia(% by mass)	IS : 4032 - 1985	Not more than 6.0	2.56
5	Total sulphur calculated as Sulphuric Anhydride (SO₃) (% by mass)	IS : 4032 - 1985	Not more than 3.5	2.94
6	Total loss on ignition (% by mass)	IS : 4032 - 1985	Not more than 4.0	1.69
7	Chloride(% by mass)*	IS : 4032 - 1985	Not more than 0.1	0.017
	Mech	anical Requirement	s	
1	Fineness (m²/kg)	IS : 4031 (Part-2) - 1999	Not less than 225	324
2	Normal Consistency (%)	IS : 4031 (Part-4) - 1988	-	29.00
3	Soundness: a) Le-chateliere expansion (mm) b) Autoclave test expansion (%)	IS : 4031 (Part-3) - 1988	Not more than 10 Not more than 0.8	1.0 0.105
4	Setting Time: a) Initial setting time (Minutes) b) Final setting time (Minutes)	IS : 4031 (Part-5) - 1988	Not less than 30 Not more than 600	130 175
5	Compressive Strength: a) 72 ± 1 Hours (3 Days) (MPa) b) 168 ± 2 Hours (7 Days) (MPa) c) 672 ± 4 Hours (28 Days) (MPa)	IS : 4031 (Part-6) - 1988	Not less than 27 Not less than 37 Not less than 53	39.7 48.0 Under Testing

Remarks: Results reported above are the average test results of all sample testing during the relevant week.



Page 1 of 1

Authorized Signatory









^{*:} Not covered under NABL Accreditation at present.