

WEEK No





## 47 LICENCE NO . CM/L-8099186

## DATE OF ISSUE 24.12.2014

CHEMICAL / PHYSICAL REQUIREMENTS	SPECIFICATION CLAUSE No.	REQUIREMENT AS PER IS No.12269 – 2013 AMENDMENT No. 6	RESULTS OBTAINED
<ul> <li>CHEMICAL REQUIREMENTS : #</li> <li>(i) Ratio of Percentage of Lime to # percentage of silica, alumina and iron oxide CaO - 0.7SO<sub>3</sub></li> </ul>	<b>5</b> 5.1	Not Greater than 1.02 And not less than 0.80	0.924
<ul><li>(ii) Ratio of percentage of alumina to that # of iron oxide</li></ul>	5.1	Not less than 0.66	1.55
(iii) Insoluble residue, percent by mass #	5.1	Not more than 4.0	2.62
(iv) Magnesia, percent by mass #	5.1	Not more than 6.0	2.24
<ul> <li>(v) Total sulphur calculated as Sulphuric # Anhydride (SO<sub>3</sub>), Percent by mass</li> </ul>	5.1	Not more than 3.5	2.58
(vi) Total loss on ignition #	5.1	Not more than 4%	2.32
<pre>(vii) Chloride, percent by mass # PHYSICAL REQUIREMENTS :</pre>	5.1 <b>6</b>	Not more than 0.1	0.034
(i) FINENESS : SP. SURFACE	6.1	Not less than 225 m2/kg	352
(ii) SOUNDNESS : a) Le-chatelier method Expansion	सन अ	Not more than 10 mm	0.50
b) Auto clave test expansion C.NO.T-0720		Not more than 0.8%	0.032
<ul><li>(iii) SETTING TIME</li><li>a) Initial Setting time in Minutes</li></ul>	6.3	Not less than 30	120
b) Final setting time in Minutes		Not more than 600	180
(iv) COMPRESIVE STRENGTH 72 ± 1 Hours (3 Days)	6.4	Not less than 27 MPa	38.2
$168 \pm 2$ Hours (7 Days)		Not less than 37 MPa	48.4
672 ± 4 Hours (28 Days)		Not less than 53 MPa	58.2

REMARKS : The test results complies with the requirements of IS: 12269–2013for 53 grade OPC for All Chemical requirements and Physical requirements including Compressive Strength up to 28 day. Test Protocol : IS:4032 and IS:4031. # Not covered under NABL Accreditation at present

Note : Results reported above are the average test results of all samples testing during relevant week.

**CERTIFIED** ISO 9001:2008 ISO 14001:2004 OHSAS 18001:2007 Steel

HOD(QC)

