





DASTAN, PALSANA, DIST. SURAT (GUJ.) LICENCE NO. CM/L-7200051895

TEST CERTIFICATE

Customer Name & Address :

Certificate (ULR) No.: TC801319000000097P

Sample Identification : Portland Pozzolana Cement (As per IS 1489 : Part 1 : 2015)

Sample Date : 02.04.2019 to 08.04.2019 (Week No : 14) Date of Issue: 17.04.2019

Sr. No	Particulars	Test Method	Requirement of IS:1489	Results Obtained
		Chemical Require	ments	
1	Loss on ignition(% by mass)	IS : 4032 - 1985	Not more than 5.0	1.88
2	Magnesia(% by mass)	IS : 4032 - 1985	Not more than 6.0	2.45
3	Sulphuric Anhydride (SO ₃)(% by mass)	IS : 4032 - 1985	Not more than 3.5	2.72
4	Insoluble Residue(% by mass)	IS : 4032 - 1985	4(100-x) x+ 100 (x=where x is the declare % age of Fly Ash)	24.85
5	Chloride(% by mass)*	IS : 4032 - 1985	Not more than 0.1	0.023
6	Declared % of Fly Ash (≤)	-	Not less than 15% and Not more than 35%	34.0
		Mechanical Require	ements	
1	Fineness (m²/kg)	IS : 4031 (Part-2) - 1999	Not less than 300	367
2	Normal Consistency (%)	IS : 4031 (Part-4) - 1988	-	32.50
3	Soundness: a) Le-chatelier expansion (mm) b) Autoclave test expansion (%)	IS : 4031 (Part-3) - 1988	Not more than 10 Not more than 0.8	0.5 0.056
4	Setting Time: a) Initial setting time (minutes) b) Final setting time (minutes)	IS : 4031 (Part-5) - 1988	Not less than 30 Not more than 600	135 180
5	Compressive Strength: a) 72 ± 1 Hours (3 Days) (MPa) b) 168 ± 2 Hours (7 Days) (MPa) c) 672 ± 4 Hours (28 Days) (MPa)	IS : 4031 (Part-6) - 1988	Not less than 16 Not less than 22 Not less than 33	28.9 37.5 Under Testing
6	Drying Shrinkage (%)	IS : 4031 (Part-10) - 1988	Not more than 0.15	Under Testing

Remarks: Results reported above are the average test results of all sample testing during the relevant week.



Page 1 of 1

Authorized Signatory









^{*:} Not covered under NABL Accreditation at present.