

## <u>JK lakshmi</u>

CEMENT Ltd. JAYKAYPURAM—307019 Dist. Sirohi, Rajasthan

LICENCE NO . CM/L-1234838



нисл. TC-5708

## ULR NO. TC-57081900000000111F WEEK No. 28

## **DATE OF ISSUE 23.07.2019**

WEEK NO. 20		DATE OF 1550	
CHEMICAL / PHYSICAL REQUIREMENTS	SPECIFICATION CLAUSE No.	REQUIREMENT AS PER IS No.1489(PART-I) – 2015	RESULTS OBTAINED
<b>CHEMICAL REQUIREMENTS :</b>	6		
(i) Loss on ignition, percent by mass, Max.	6.1	5.0	2.54
(ii) Magnesia, percentage by mass, Max	6.1	6.0	2.49
<ul><li>(iii) Sulphuric Anhydride (SO<sub>3</sub>), percent by mass, Max</li></ul>	6.1	3.5	2.47
(iv) Insoluble Residue, percent by mass Max.	6.1	4(100-x) x+ 100 (x=where x is the declare % age of Fly Ash)	23.28
(v) Insoluble Residue, percent by mass Min	6.1	0.6 x	15.0
(vi) Declared % of Fly Ash	5 & 9.1	Not less than 15% and Not more than 35%	28+/-3
(vii) Chloride, percent by mass	9.2	Not more than 0.1	0.044
PHYSICAL REQUIREMENTS :	7		
(i) FINENESS : SP. SURFACE	7.1	Not less than 300 m2/kg	350
<ul><li>(ii) SOUNDNESS :</li><li>a) Le-chatelier method Expansion</li></ul>	7.2	Not more than 10 mm	0.50
b) Auto clave test expansion		Not more than 0.8%	0.050
<ul><li>(iii) SETTING TIME</li><li>a) Initial Setting time in Minutes</li></ul>	7.3	30 minutes, minimum	140
b) Final setting time in Minutes		600 minutes, maximum	180
(iv) COMPRESIVE STRENGTH 72 ± 1 Hours (3 Days)	7.4	16 Mpa, Min	28.0
$168 \pm 2$ Hours (7 Days)		22 Mpa, Min	37.0
672 ± 4 Hours (28 Days) (v) Drying Shrinkage	7.5	33 Mpa, Min Not be more than 0.15%	Under Testing <b>Under Testing</b>
REMARKS : The test results complies with the requirements of IS: 1489(Part-I) : 2015 for all Chemical requirements and Physical requirements including Compressive Strength up to 7-days. Note : Results reported above are the average test results of all samples testing during relevant week.			

CERTIFIED ISO 9001:2015 ISO 14001:2015 OHSAS 18001:2007 Steer

HOD(QC)

