

JSW Cement Limited TEST REPORT

Portland Slag Cement as per IS 455:1989

REF.: JSW/QA/2014 47 DATE: **02-12-2016**

WEEK NO.: 47 18-11-2016 to 24-11-2016

| CHARACTERISTIC | RESULTS OBTAINED | REQUIREMENT OF IS455:1989 |
|--|------------------|---------------------------|
| | | |
| (A) CHEMICAL COMPOSITION | | |
| (i) Magnesia (MgO), % by mass | 4.56 | 10.0 Maximum |
| (ii) Insoluble Residue, % by mass | 0.37 | 4.0 Maximum |
| (iii) Sulphuric Anhydride (SO ₃) % by mass | 2.34 | 3.0 Maximum |
| (iv) Sulphide Sulphur (S) | 0.22 | 1.5 Maximum |
| (v) Loss on Ignition % by mass | 0.80 | 5.0 Maximum |
| (vi) Total Chloride (Cl), % by mass | 0.014 | 0.10 Maximum |
| (B) PHYSICAL TESTING | | |
| 1. Fineness of Cement | | |
| Sp.Surface blaine (m²/kg) | 344 | 225 m²/kg minimum |
| 2. Soundness | | |
| Le-Chatelier Expansion (mm) | 0.54 | 10 mm Maximum |
| Autoclave Expansion (%) | 0.04 | 0.8 % Maximum |
| 3. Setting Time | | |
| Initial (in Minutes) | 196 | Not less than 30 minutes |
| Final (in Minutes) | 247 | Not more than 600 minutes |
| 4. Compressive Strength (MPa) | | |
| (a) At 72 ± 1 Hrs. | 23.70 | 16 MPa Minimum |
| (b) At 168 ± 2 Hrs. | 34.68 | 22 MPa Minimum |
| (c) At 672 ± 4 Hrs. | Result Awaited | 33 MPa Minimum |
| | : | |

Remarks:

- 1. Temperature during testing $27 \pm 2^{\circ}$ c.
- 2. Portland Slag Cement conforms to the requirement of IS 455-1989 in all respects.

Address:

JSW CEMENT LIMITED

Village- Khar Karavi, Post Office- Gadab

Taluka- Pen, District- Raigad

402107, Maharashtra. +91 2143 277601/2

Associate Vice President