



SANGHI INDUSTRIES LIMITED
QUALITY CONTROL LABORATORY

Sanghipuram - 370 511.

Turning Dreams into Concrete Reality Tal. : Abdasa, Dist. : Kutch, State : Gujarat



CM/L 7431062

(NABL ACCREDITED LABORATORY)

T - 1233, T - 1234

Phone (02831) 274131, 274132, 274135, Fax : (02831) 274106,274115, e-mail : info@sanghicement.com

Page No. : 1/1
Certificate No. : CMD/OPC/02.01.2019
Lot Create Date : 02.01.2019
Material :
Lab Code : 350/CM/19
Sample Received From : Packing Plant
Address : SIL-Sanghipuram
Reference : Day Average Com.Despatch
During of testing Period : 02.01.2019 To 30.01.2019
Tested as per : IS 4031 & IS 4032
Date of Sample : 02.01.2019
Month : 01
Week : 01

NABL/TP/F30

Issue No.6, Amnd.No.: 03, Eff. Dt. : 31.10.2016

TEST CERTIFICATE

PARAMETERS TESTED	REQUIREMENTS AS PER IS 269:2015	RESULTS OBTAINED
1.Chemical Testing		
Loss on Ignition	LESS THAN 4.00%	1.69
Insoluble Residue	LESS THAN 5.00%	1.74
SO ₃	LESS THAN 3.50%	3.04
MgO	LESS THAN 6.00%	2.73
Chloride	LESS THAN 0.10%	0.052
LSF	0.80% To 1.02%	0.86
C3A	-	7.36
2.Mechanical Testing		
Specific Surface	MORE THAN 225.00m ² /kg	304
Normal Consistency		28.0
Setting Time - Initial	MORE THAN 30.00min	125
Setting Time - Final	LESS THAN 600.00min	180
Soundness Lechatelier	LESS THAN 10.00MM	1.5
Soundness Autoclave	LESS THAN 0.80%	0.10
Comp. Strength - 24 Hrs. *		23.0
Comp. Strength - 72 ± 1 Hrs.	MORE THAN 27.00MPa	37.5
Comp. Strength - 168 ± 2 Hrs.	MORE THAN 37.00MPa	45.5

SANGHI CEMENT * SANGHI CEMENT

SANGHI CEMENT * SANGHI CEMENT

Conditions :

- The test results pertain to the sample received only.
- This report is being issued with a specific understanding that SIL QC LAB will not in any way be involved in action following the interpretation of above results.
- This report shall not be re-produced except in full without written approval from SIL QC LAB.

* 1 Day testing is out of NABL scope.

Authorised Signatory

Quality Manager