

SANGHI INDUSTRIES LIMITED QUALITY CONTROL LABORATORY

Sanghipuram - 370 511.

Turning Dreams into Concrete Reality Tal.: Abdasa, Dist.: Kutch, State: Gujarat

CM/L 7431062 (NABL ACCREDITED LABORATORY)

T - 1233, T - 1234

A N G

Н

C

M E

N T

S

N G H

C E M E

Phone (02831) 274131, 274132, 274135, Fax: (02831) 274106,274115, e-mail: info@sanghicement.com

Page No. : 1/1

Certificate No. : CMD/OPC/16.01.2019

Lot Create Date : 16.01.2019

Material : CMOPC53

Lab Code : 346/CM/16

Sample Received From : Packing Plant

Address : SIL-Sanghipuram

Reference : Day Average Com.Despatch During of testing Period : 16.01.2019 To 13.02.2019

Tested as per : IS 4031 & IS 4032

Date of Sample : 16.01.2019

Month : 01 Week : 03

NABL/TP/F30

Issue No.6, Amnd.No.: 03, Eff. Dt.: 31.10.2016

SANGHI CEMENT * SANGHI CEMENT

TEST CERTIFICATE		
PARAMETERS TESTED	REQUIREMENTS AS PER IS 269:2015	RESULTS OBTAINED
1.Chemical Testing		
Loss on Ignition	LESS THAN 4.00%	1.89
Insoluble Residue	LESS THAN 5.00%	2.34
SO3	LESS THAN 3.50%	2.92
MgO	LESS THAN 6.00%	2.73
Chlolride	LESS THAN 0.10%	0.048
LSF	0.80% To 1.02%	0.82
АМ	MORE THAN 0.66%	1.53
СЗА	-	9.62
2.Mechanical Testing		
Specific Surface	MORE THAN 225.00m2/kg	305
Normal Consistency		29.5
Setting Time - Initial	MORE THAN 30.00min	120
Setting Time - Final	LESS THAN 600.00min	180
Soundness Lechatelier	LESS THAN 10.00MM	1.0
Soundness Autoclave	LESS THAN 0.80%	0.08
Comp. Strength - 24 Hrs. *		20.5
Comp. Strength - 72 ± 1 Hrs.	MORE THAN 27.00MPa	36.0
Comp. Strength - 168 ± 2 Hrs.	MORE THAN 37.00MPa	48.0

Conditions:

- 1. The test results pertain to the sample received only.
- 2. This report is being issued with a specific understanding that SIL QC LAB will not in any way be involved in action following the interpretation of above results.
- 3. This report shall not be re-produced except in full without written approval from SIL QC LAB.
- * 1 Day testing is out of NABL scope.

Authorised Signatory

Quality Manager