



Turning Dreams into Concrete Reality

**SANGHI INDUSTRIES LIMITED
QUALITY CONTROL LABORATORY**

Sanghipuram - 370 511.

Tal. : Abdasa, Dist. : Kutch, State : Gujarat



T - 6817

CML-3744164

(NABL ACCREDITED LABORATORY)

Phone (02831) 274131, 274132, 274135, Fax : (02831) 274106,274115, e-mail : info@sanghiment.com

Page No. : 1/1
 Certificate No. : CMD/PPC/04.03.2021
 Lot Create Date : 05.03.2021
 Material : CMPPC
 Lab Code : 63CM/3-2021
 Sample Received From : Packing Plant
 Address : SIL-Sanghipuram
 Reference : Day Average Com. Dispatch
 Tested as per : IS 4031 & IS 4032
 Date of Sample : 04.03.2021
 Date of Testing : 05.03.2021
 Month : 03 Rh : More than 65%
 Week : 09 Temperature : 27°C+ 2
 Issue Date :

NABL/TP/F30

Issue No.1, Amnd.No.: 03, Eff. Dt. : 19.08.2019

TEST CERTIFICATE

PARAMETER TESTED	RESULTS OBTAINED	UOM	TEST METHOD	SPECIFICATION (IS:1489:2015)
1.PPC Chemical Testing				
PPC-LOI	3.61	%	IS 4032:1985	LESS THAN 5.00
PPC - MGO	2.51	%	IS 4032:1985	LESS THAN 6%
PPC_SO3	2.53	%	IS 4032:1985	LESS THAN 3.50
PPC -CI	0.033	%	IS 4032:1985	LESS THAN 0.10
PPC Flyash Content	32.0	%	-	15% to 35%
IR_PPC X+4.0(100-X)/100 & 0.60*X,MIN	22.76	%	IS 4032:1985	X + 4.0 (100-X)/100, Max & 0.60 * X Min
2.PPC Mechanical Testing				
PPC - Specific Surface	345	M2/Kg		MORE THAN 300
PPC-Normal Consistency	29.25	%	IS 4031(Part 4):1988	N.A.
PPC -Initial Setting Time	125	min	IS 4031(Part 5):1988	MORE THAN 30
PPC -Final Setting Time	175	min	IS 4031(Part 5):1988	LESS THAN 600
Le-Chatlier Expansion LCE_PPC	0.50	mm	IS 4031(Part 3):1988	LESS THAN 10
Autoclave Expansion - PPC	0.180	%	IS 4031(Part 3):1988	LESS THAN 0.80
1 Days Compressive Strength - PPC	18.0	MPa		N.A.
3 Days Compressive Strength - PPC	29.7	MPa	IS 4031(Part 6):1988	MORE THAN 16.0
7 Days Compressive Strength - PPC	38.5	MPa	IS 4031(Part 6):2005	MORE THAN 22.0

Conditions :

- The test results pertain to the sample received only.
- This report is being issued with a specific understanding that SIL QC LAB will not in any way be involved in action following the interpretation of above results.
- This report shall not be re-produced except in full without written approval from SIL QC LAB.
- 1 Day testing is out of NABL scope.
- Insoluble Residue limit as per % Fly Ash declaration

Authorised Signatory

Quality Manager