



TRUST. LEGACY. FOREVER.

KALBURGI CEMENT PVT. LTD.

Corporate Office: 8-2-626, Reliance Majestic Building, Road No. 10, Banjara Hills, Hyderabad – 500 034, A.P., India. Ph.: +91 40 3006999; Fax: +91 40 30006955

Works: Chatrasala (V), Kharchkhed (Post) - 585 320, Chincholi (Tq.), Gulbarga Dist.

IS:269



CM/L :4578077

TEST CERTIFICATE (OPC - 43 Grade)

Product : VICAT - PERFORMATE

Week No: 29

Despatched from: 16.07.2021 to 22.07.2021

A. PHYSICAL REQUIREMENTS	RESULTS	As per IS 269 – 2015
Fineness:		
a. Specific Surface (m ² /kg)	277	Not less than 225
b. Normal Consistency (%)	30.00	-----
Soundness:		
a. By Le-Chatelier Method (mm)	1.71	Not more than 10 mm
b. By Autoclave (%)	0.045	Not more than 0.8 %
Setting Time:		
a. Initial Setting Time (minutes)	145	Not less than 30
b. Final Setting Time (minutes)	245	Not more than 600
Compressive Strength (MPa)		
a. 3 days	34.00	Not less than 23
b. 7 days	43.00	Not less than 33
c. 28 days	54.86	Not less than 43 & Not more than 58
B. CHEMICAL REQUIREMENTS		
a. Lime Saturation Factor	0.87	0.66 – 1.02
b. Aluminum Modules	1.09	Not less than 0.66
c. Insoluble Residue (%)	2.56	Not more than 5.0
d. Magnesia (%)	0.97	Not more than 6.0
e. Sulphuric Anhydride (%)	2.42	Not more than 3.5
f. Loss on Ignition (%)	2.86	Not more than 5.0
g. Chlorides (%)	0.030	Not more than 0.1
h. Alkali Content (%)	0.45	Not more than 0.6
i. Temperature During Testing °C	26.50	27 ± 2

Section In-Charge (Q.C)

Authorised Signature