

KALBURGI CEMENT PVT. LTD.

<u>Corporate Office</u>: 8-2-626, Reliance Majestic Building, Road No. 10, Banjara Hills, Hyderabad – 500 034, A.P., India. Ph.: +91 40 3006999; Fax: +91 40 3006955



Works : Chatrasala (V), Kharchkhed (Post) - 585 320, Chincholi (Tq.), Gulbarga Dist.

TEST CERTIFICATE (OPC - 43 Grade)

Product : VICAT - PERFORMATE

Week No: 36

Despatched from: 31.08.2020 to 06.09.2020

| A. PHY | SICAL REQUIREMENTS | RESULTS | As per IS 269 – 2015 |
|----------------------------|---|---------|-------------------------------------|
| Fineness: | | | |
| a. | Specific Surface (m2/kg) | 279 | Not less than 225 |
| b. | Normal Consistency (%) | 29.50 | |
| Soundness: | | | |
| a. | By Le-Chatelier Method (mm) | 1.00 | Not more than 10 mm |
| b. | By Autoclave (%) | 0.047 | Not more than 0.8 % |
| Setting Time: | | | |
| a. | Initial Setting Time (minutes) | 160 | Not less than 30 |
| b. | Final Setting Time (minutes) | 250 | Not more than 600 |
| Compressive Strength (MPa) | | | |
| a. | 3 days | 34.20 | Not less than 23 |
| b. | 7 days | Awaited | Not less than 33 |
| C. | 28 days | Awaited | Not less than 43 & Not more than 58 |
| B. CHEMICAL REQUIREMENTS | | | |
| a. | Lime Saturation Factor | 0.87 | 0.66 – 1.02 |
| b. | Aluminum Modules | 1.10 | Not less than 0.66 |
| c. | Insoluble Residue (%) | 2.57 | Not more than 5.0 |
| d. | Magnesia (%) | 0.98 | Not more than 6.0 |
| e. | Sulphuric Anhydride (%) | 2.47 | Not more than 3.5 |
| f. | Loss on Ignition (%) | 2.89 | Not more than 5.0 |
| g. | Chlorides (%) | 0.030 | Not more than 0.1 |
| h. | Alkali Content (%) | 0.52 | Not more than 0.6 |
| i. | Temperature During Testing ⁰ C | 27.00 | 27 ± 2 |

17. of:12

Section In-Charge (Q.C)

Authorised Signature