



TRUST. LEGACY. FOREVER.

**KALBURGI CEMENT PVT. LTD.**Corporate Office: 8-2-626, Reliance Majestic Building, Road No. 10, Banjara Hills,  
Hyderabad – 500 034, A.P., India. Ph.: +91 40 3006999; Fax: +91 40 30006955Works : Chatrasala (V), Kharchkhed (Post) - 585 320, Chincholi (Tq.), Gulbarga Dist.

IS:1489 (Part-1)



CM/L :4596685

**TEST CERTIFICATE (PPC)**

Product : VICAT - DURAMATE

Week No: 26

Despatched From : 25-06-2022 TO 01-07-2022

A. PHYSICAL REQUIREMENTS	RESULTS	As per IS 1489 (Part-1) 2015
<b>Fineness:</b>		
a. Specific Surface (m <sup>2</sup> /kg)	327	Not less than 300
b. Normal Consistency (%)	32.5	-----
<b>Soundness:</b>		
a. By Le-Chatelier Method (mm)	0.75	Not more than 10 mm
b. By Autoclave (%)	0.03	Not more than 0.8 %
<b>Setting Time:</b>		
a. Initial Setting Time (minutes)	135	Not less than 30
b. Final Setting Time (minutes)	240	Not more than 600
<b>Compressive Strength (MPa)</b>		
a. 3 days	25.04	Not less than 16
b. 7 days	Awaited	Not less than 22
c. 28 days	Awaited	Not less than 33
d. Drying Shrinkage(%)	Awaited	Not more than 0.15
e. Flyash Addition (%)	34.54	Not more than 35
<b>B. CHEMICAL REQUIREMENTS</b>		
a. Insoluble Residue (%)	31.40	$X+4(100-X)/100$ ; X = % of Flyash
b. Magnesia (%)	0.92	Not more than 6.0
c. Sulphuric Anhydride (%)	2.32	Not more than 3.5
d. Loss on Ignition (%)	2.52	Not more than 5.0
e. Alkali Content (%)	0.64	Not more than 0.90
i. Temperature During Testing °C	27.00	27 ± 2

Section In-Charge (Q.C)

Authorised Signature